



## ■ HengMi Model Components Series

Rubber	
NBR	Resistant to oil, pressure and wear, good elasticity and mechanical strength; applicable to the mediums including water, oil, alcohol, etc from $-20^{\circ}\text{C}$ to $100^{\circ}\text{C}$
EPDM	Resistant to high or low temperatures, ozone and chemicals; applicable to weak acids with temperatures from $-30^{\circ}\text{C}$ to $150^{\circ}\text{C}$
Viton	Resistant to heat, oil, medicine and chemical reagents, acid and alkali with medium corrosive degrees; applicable to the corrosive mediums from $-20^{\circ}\text{C}$ to $180^{\circ}\text{C}$
Silica Gel	Resistant to ozone, aging, acetic acid, ammonia and alcohol; applicable to alcohol, alkali, etc from $150^{\circ}\text{C}$ to $210^{\circ}\text{C}$
Chlorinated Rubber	Resistant to Freon, petroleum; applicable to inorganic acid, alkali, ranging from $-30^{\circ}\text{C}$ to $130^{\circ}\text{C}$